

Technical Data Sheet

updated

29.08.2014

checked

29.08.2014

Article-No PES-Elastan-Dekotex mit "INKTeX+® FL Ausrüstung"

8484PBR

finishing for direct print, with flame retardant treatment, with soft handle equal elongation in length and width

Material 91 % Polyester
9 % Elastan

Stock widths app. 310 cm

Possible widths app. 310cm

Finishing rolled on paper cores

Packaging wrapped with foil

Ecology according to Öko-Tex Standard 100, product class IV

Weight

acc. to DIN EN 12127 230.00 [g/m²] +- 3 [%]

Tearing strength

Maximum tensile elongation, longitudinal direction

acc. to DIN EN ISO 13934-1 130.00 [%] +- 20 [%]

Maximum tensile elongation, cross direction

acc. to DIN EN ISO 13934-1 130.00 [%] +- 20 [%]

Maximum tearing strength, longitudinal direction

acc. to DIN EN ISO 13934-1 min. 640.00 [N/5 cm]

Maximum tearing strength, cross direction

acc. to DIN EN ISO 13934-1 min. 640.00 [N/5 cm]

We do not accept liability for errors. Printing mistakes and changes are reserved.

Please pay attention to our general considerations regarding fabrication at www.g-o-friedrich.com

Page 1 / 1