

Technical Data Sheet

updated
checked

05.11.2015
05.11.2015

Article-No PES-Dekotex mit "INKTeX+® FL Ausrüstung"

7096FLBS
with INKTeX+BS® finishing for
direct print with diverse inks,
with flame retardant treatment

Material 100 % Polyester

Stock widths app. 253 cm, 303 cm

Finishing rolled on paper cores

Packaging wrapped with foil

Ecology according to Öko-Tex Standard 100,
product class IV

Bleaching do not bleach

Ironing Do not iron

Washing 40° Machine wash, normal

Drying tumbler dry with low temperature (gently)

**Professional textile
cleaning** professional dry-cleaning



Weight
acc. to DIN EN 12127 330.00 [g/m²] +- 3 [%]

Shrinkage

Heat Shrinkage, 195 °C, 90 sec,
lengthwise
acc. to AA 25-02 -2.50 [%] +- 1 [%]

Heat Shrinkage, 195 °C, 90 sec,
crosswise
acc. to AA 25-02 -2.50 [%] +- 1 [%]

Georg+Otto Friedrich

EUROPAS GROSSE WIRKWARENPRODUZENTEN

Tearing strength

Maximum tensile elongation, longitudinal direction

acc. to DIN EN ISO 13934-1 70.00 [%] +- 20 [%]

Maximum tensile elongation, cross direction

acc. to DIN EN ISO 13934-1 35.00 [%] +- 20 [%]

Maximum tearing strength, longitudinal direction

acc. to DIN EN ISO 13934-1 min. 450.00 [N/5 cm]

Maximum tearing strength, cross direction

acc. to DIN EN ISO 13934-1 min. 2000.00 [N/5 cm]

We do not accept liability for errors. Printing mistakes and changes are reserved.

Please pay attention to our general considerations regarding fabrication at www.g-o-friedrich.com

Page 2 / 2

Georg + Otto Friedrich GmbH
Waldstraße 73, 64846 Groß-Zimmern
Telefon: +49 (0) 60 71 492-0
Telefax: +49 (0) 60 71 492-39
www.g-o-friedrich.com

HRB 93510 Darmstadt
UST-ID-Nr.: DE 296663791
Geschäftsführer
Lothar Vorbeck, Peter Vorbeck,
Kai Trippel

Volksbank Odenwald eG
IBAN: DE34 5086 3513 0000 0799 10
BIC: GENODE51MIC
European Money Transfer
Swift: GENODEFF

Sparkasse Dieburg
IBAN: DE44 5085 2651 0138 1111 17
BIC: HELADEF1DIE



73 100 1388